

# Zirblast®

TECHNICAL DATA SHEET

- Ceramic beads specifically suited to many impact surface treatments.
- High recyclability, efficient whether used in wheel-blast or air-blast (dry or wet) systems.

2012/04

## TYPICAL CHEMICAL ANALYSIS

ZrO <sub>2</sub>	60 to 70 %
SiO <sub>2</sub>	28 to 33 %
Al <sub>2</sub> O <sub>3</sub>	< 10 %

Chemical analysis carried out by X-Ray fluorescence on melting sample

## CRYSTAL STRUCTURE

Zirconia	68 %
Vitreous phase	32 %

Typical values


## PHYSICAL PROPERTIES

Specific gravity	3.85 g/cm <sup>3</sup>
Bulk density	2.30 kg/l
Vickers hardness (Equivalent HRC 50 at 65)*	700 HV1

\* Statistical measurement

- White color and smooth surface
- High toughness, but not very aggressive with equipment and tools
- Chemically inert, non contaminating for treated parts
- Low dust production

## DESIGNATION AND AVAILABLE SIZES



**INDUSTRY STANDARD** \_\_\_\_\_ NF L 06-824


**SPECIFICATION** \_\_\_\_\_ DS SP BE 01

**SAFETY DATA SHEET** \_\_\_\_\_ DS MS BE 11

## PACKAGING

25 kg plastic jerrycan

500 kg or 1 ton big-bag



Zirblast B60 being used for steel descaling

## MAIN APPLICATIONS

- Tool cleaning
- Stainless steel and light alloy finishing
- Deburring
- Difficult descaling
- Paint or coating stripping
- Surface or galvanization etching

**For higher performance applications, Zirshot is recommended (for example shot peening).**

*Saint-Gobain ZirPro is the expert in zirconia-based materials for industrial applications. From our global network of manufacturing, commercial and research facilities, we serve leading customers through long-term and trust-based relationships.*



Les informations, objet de cette fiche produit, sont données à titre indicatif et n'ont aucune valeur contractuelle. / The contents of this data sheet are given in good faith but without warranty.